



Typical Technical Data WAM® 60 G

Classification	Reduced Cement Gun Mix
Installation Method	Dry Gunning
Pre-Dampening Water, (%)	4
Amount Required for Gunning, pcf	146
Density (pcf)	
after 230 °F	152
after 1500 °F	146
Modulus of Rupture (psi)	
after 230 °F	1,880
after 1500 °F	1,570
Cold Crushing Strength (psi)	
after 230 °F	11,150
after 1500 °F	7,890
Permanent Linear Change (%)	
after 1500 °F	-0.2
after 2500 °F	+1.2
Calculated Chemical Analysis (%)	
Aluminum Oxide	59.6
Silicon Dioxide	33.3
Titanium Oxide	2.1
Iron Oxide	1.0
Calcium Oxide	3.5
Magnesium Oxide	0.2
Total Alkali	0.2

Data on this table represents typical properties, and cannot be used for specification purposes.