



Technical Data
WAM® 75 M
(Dry Bonding Mortar)

Maximum Recommended Temperature	3100°F
Pyrometric Cone Equivalent, P.C.E.	Cone 35+
Screen Sizing % Passing 35 Mesh	99+
Approximate Water Addition Needed for:	
Troweling (May be Adjusted to Suit)	20%
Dipping (May be Adjusted to Suit)	25%
<u>Approximate Chemical Analysis:</u>	
Alumina	76.1%
Silica	21.0
Titania	2.7
Iron Oxide	1.1
Lime	< 0.1
Magnesia	<0.1
Total Alkali	<0.5