



Technical Data
WAM® HTC AA
(High Temperature Cover & Patching Mix)

Maximum Recommended Temperature	3200°F
Screen Sizing % Passing 150 Mesh	99+
Approximate Water Addition Needed for:	
Painting (May be Adjusted to Suit)	25%
Troweling (May be Adjusted to Suit)	20%
Drying Shrinkage (230 °F)	Negligible
<u>Approximate Chemical Analysis:</u>	
Alumina	95.9%
Silica	<0.1
Titania	<0.1
Iron Oxide	<0.1
Lime	<0.1
Magnesia	<0.1
Total Alkali	4.1